



- Universally applicable, diffusion open vapour barrier membrane
- Tear resistant, stable in shape and slightly transparent, with cutting marker
- Verified system accessories incl. PAVATEX system guarantee

Delivery form

Roll width [m]	Roll length [m]	Roll area [m ²]	Roll weight [kg]
1.50	50.00	75.00	9

Field of application



Technical data

Material	Polypropylene fleece with polyolefin copolymer coating	
Thickness [mm]	0.40	
Vapour diffusion resistance coefficient μ	7500	
s_d value [m]	3.5	
Specific weight [g/m ²]	110	
Fire behaviour (EN 13501-1)	Class E	
Fire index according to VKF (BKZ)	5.2	
Stretch [%]	lengthwise	50
	across	60
Maximum tensile force [N/5cm]	lengthwise	180
	across	140
Resistance to tearing (nail shank) [N]	lengthwise	130
	across	140
CE	EN 13984	

Product description

PAVATEX DB 3.5 is used as an airtight vapour barrier in permeable roof and wall constructions. PAVATEX DB 3.5 is installed on the warm side of the thermal insulation. Gluing the membrane joints, and gluing the connections and penetrations, is carried out using PAVATEX sealing products.

Storage

Store the rolls dry and cool, lying down or upright, protected from sunshine and humidity.



PAVATEX System accessories

- PAVACOLL 310/600
- PAVABOND
- PAVATAPE 12
- PAVATAPE FLEX
- PAVAFIX

You will find details on usage and installation guidelines in the sealing brochure.

